

FLEXIBLE ADHESIVE MORTAR

**PRODUCT NAME**

CLINK' FLEX

STANDARD

UNE - EN 12004

COMPOSITION

Grey/white cement, sand, large amounts of resin and various additives.

DESCRIPTION

CLINK' FLEX is a flexible adhesive mortar ideal for small or large format, high-resistance floors and ceilings of ceramic, marble, stone or similar. Ideal for use with porcelain.

Available in grey or white.





FLEXIBLE ADHESIVE MORTAR

CLINK' FLEX

METHOD OF APPLICATION

PREPARATION:

- Ensure the surfaces to be tiled are in good condition and clean, that there are no traces of grease or dust, and that they are mechanically resistant.
- Respect the drying times of the surfaces: 48 hours for cement render, 2 months after the completion of building work for new concrete structures.

PRODUCT PREPARATION:

- Sprinkle CLINK'FLEX into clean water. Mix by hand or with an electric mixer (on a low setting), until you have a smooth, even mixture with no lumps.
- Leave the mixture to stand for 2 minutes.

APPLICATION:

- CLINK' FLEX should be applied with an appropriate toothed trowel. Using the flat side of the trowel, apply a thin coat of adhesive, pressing hard onto the surface. Next, even it out using the toothed part of the trowel at an appropriate angle.
- Press on each tile to ensure full and even contact with the adhesive.



ADVANTAGES

High yield

High deformability

Excellent adhesion

Maximum safety

TECHNICAL DATA

WATER / PRODUCT RATIO:	7-9 l/sack
MIXTURE STANDING TIME:	2 min
CORRECTION TIME:	40 min
USE WITHIN:	4H
WALK ON ALTER:	24H
YIELD:	3,5 kg/m ²
MIXING SPEED:	500 rpm
APPLICATION TEMPERATURE:	5 °C - 40 °C

PACKAGING



20 KG/SACK



64 SACKS/PALLET



25 TN



STORAGE AND PRESERVATION

- Store the product on a flat surface and never outdoors. Keep dry and out of direct sunlight.
- Use within 12 months of the date of manufacture.

LEGAL NOTICE: This information, in particular the recommendations relating to product application and the technical data, is based on our experience and current knowledge as well as the suggested uses and common applications of our products, and is subject to the final conditions of the site or the application of the products. GYPROD is not liable for the use of the products by third parties, or for the results obtained.
The GYPROD quality guarantee is limited exclusively to the product supplied.