


SELF-LEVELLING MORTAR



PRODUCT NAME	CLINK' SELF LEVELING
STANDARD	UNE - EN 13813
COMPOSITION	Grey cement, limestone aggregate and chemical additives that provide self-levelling properties.
DESCRIPTION	CLINK' SELF-LEVELLING is a self-levelling mortar for laying ceramic tiles, carpets, laminate flooring, etc.



SELF-LEVELLING MORTAR

CLINK' SELF LEVELING

METHOD OF APPLICATION

PREPARATION:

- The base surface must be tough, hard and rough if possible. It must be free of dust, paint, grease, etc.

APPLICATION:

- Before beginning pouring, mark the levels for the self-levelling finish to establish the required thickness. This can be done with the help of a laser level, water level, etc.
- It is important to create expansion joints at critical points and place perimeter joints, as well as respecting the building's expansion joints.
- Treatment of the mortar: take all the measures necessary to prevent the mortar drying out quickly.
- Do not walk on it until 48 hours after laying, and do not place any weight on it until 7 days after application.
- Any coating, with an appropriate cement adhesive, should be laid 3 weeks after application. Before laying the coating, clean the surface using a floor grinding and dust suction device to remove any dust from the mortar.



ADVANTAGES

High yield

Excellent self-levelling properties

Can be applied to old or new surfaces

TECHNICAL DATA

WATER FOR MIXING:	12 - 14%
USE WITHIN:	1H
SETTING STARTS AT:	330 min
SETTING ENDS AT:	525 min
DRYING TIME:	24H

PACKAGING



20 KG/SACK



64 SACKS/PALLET



25 TN



STORAGE AND PRESERVATION

- Store the product on a flat surface and never outdoors. Keep dry and out of direct sunlight.
- Use within 12 months of the date of manufacture.

LEGAL NOTICE: This information, in particular the recommendations relating to product application and the technical data, is based on our experience and current knowledge as well as the suggested uses and common applications of our products, and is subject to the final conditions of the site or the application of the products. GYPROD is not liable for the use of the products by third parties, or for the results obtained.
The GYPROD quality guarantee is limited exclusively to the product supplied.