

PLASTER

E-30 / E-35

**PRODUCT NAME**

GYPS' CLASSICAL E-30 / GYPS'CLASSICAL E-35

STANDARD

UNE - EN 13279-1

DESCRIPTION

GYPS' CLASSICAL is a plaster for making pre-fabricated components, attaching such components, and touching-up and finishing work.

The product consists of a very fine powder that provides a high level of perfection and whiteness.



PLASTER E-30 / E-35

GYPS' CLASSICAL E-30 / GYPS'CLASSICAL E-35

RANGE

There are two versions available that have slightly different work times: one, also known as construction plaster, is slow setting (ideal for touching-up and finishing jobs), and the other is quick setting and apt for use on production lines manufacturing prefabricated components, such as plasterboard, mouldings, etc.

METHOD OF APPLICATION

PREPARATION:

- The surface should be free of dust, particles, efflorescence, mould release oil and other residue that may adversely affect the adherence of the coating. Clean the surface before use if you consider it necessary.

PRODUCT PREPARATION:

- Sprinkle the required amount of GYPS' CLASSICAL into clean water.
- Mix manually until you have obtained a smooth, even paste.

APPLICATION:

- Apply the product with a trowel until you have the desired finish.
- Later application of paint must be done following the paint manufacturer's recommendations.



ADVANTAGES

Simple application

High yield

Excellent mechanical properties

TECHNICAL DATA

PURITY INDEX:	≥ 90 %
GRANULOMETRY:	0-200 µ
START OF WORK:	immediate
USE WITHIN:	10-20 min
APPLICATION TEMPERATURE:	5 °C - 40 °C

PACKAGING



25 KG/SACK



BIG BAG



48 SACKS/PALLET



25 TN



STORAGE AND PRESERVATION

- Store the product on a flat surface and never outdoors. Keep dry and out of direct sunlight.
- Use within 12 months of the date of manufacture.

LEGAL NOTICE: This information, in particular the recommendations relating to product application and the technical data, is based on our experience and current knowledge as well as the suggested uses and common applications of our products, and is subject to the final conditions of the site or the application of the products. GYPROD is not liable for the use of the products by third parties, or for the results obtained.
The GYPROD quality guarantee is limited exclusively to the product supplied.