

STRONG-BOND PLASTER

**PRODUCT NAME**

GYPS' STRONG PLASTER BOARD FIXING

STANDARD

UNE - EN 14496

DESCRIPTION

GYPS' STRONG PLASTER BOARD FIXING is an adhesive for directly sticking laminated plasterboard or processed plasterboard with incorporated insulation.





STRONG-BOND PLASTER

GYPS' STRONG PLASTER BOARD FIXING

METHOD OF APPLICATION

PREPARATION:

- The surface must have a normal level of absorption, and be dry and free of dust, dirt and any other contaminating element.

PRODUCT PREPARATION:

- Sprinkle GYPS' STRONG PLASTER BOARD FIXING into the correct amount of clean water for the quantity of product to be mixed.
- Leave it to stand for around 10 minutes to let the plaster hydrate correctly.
- We recommend you mix it with an electric mixer for 1-2 minutes until you get a thick mixture without lumps.

APPLICATION:

- Use a spatula or trowel to apply the plaster in blobs of around 10 cm in diameter and approximately 40 cm apart both vertically and horizontally.
- In the case of fibrous insulating materials (glass wool, stone wool), first apply some bands of GYPS' STRONG PLASTER BOARD FIXING and then apply the blobs of plaster to these bands.
- Once the panel has been put in place, the actual glued surface should correspond to approximately 15% of the total surface of the panel.



ADVANTAGES

Perfect adhesion of boards to supports

Plane-defect repair

Good-quality finish

TECHNICAL DATA

SETTING TIME:	1H 30min
DRYING TIME:	24 H
MIXTURE STANDING TIME:	10 min
WATER / PRODUCT RATIO:	13 - 15 l/sack
APPLICATION TEMPERATURE:	5 °C - 40 °C

PACKAGING



25 KG/SACK



48 SACKS/PALLET



25 TN



STORAGE AND PRESERVATION

- Store the product on a flat surface and never outdoors. Keep dry and out of direct sunlight.
- Use within 12 months of the date of manufacture.

LEGAL NOTICE: This information, in particular the recommendations relating to product application and the technical data, is based on our experience and current knowledge as well as the suggested uses and common applications of our products, and is subject to the final conditions of the site or the application of the products. GYPROD is not liable for the use of the products by third parties, or for the results obtained.
The GYPROD quality guarantee is limited exclusively to the product supplied.